

## Rapid Build

### Heavy-duty textured waterproof sprayable & brushable coating for surface protection

LRM Products VerseGrip – Rapid Build is a fluid applied polymer modified emulsion for improved traction in trafficable areas. VerseGrip is recommended for a cost effective way to provide long term grip and cushioning of trafficable areas. It is commonly used for protecting livestock from injury during transport and processing.

VerseGrip Rapid Build when cured fully adheres to the substrate to which it is applied, providing a flexible long wearing surface. VerseGrip Rapid Build is not affected by sunlight, water or occasional chemical spills. VerseGrip Rapid Build is a single component, cold applied coating, applied alone or in conjunction with VerseGrip Bulk Build or Quick Set.

VerseGrip Rapid Build is a polymer modified emulsion formulated for application by brush, roller or squeegee. Applications include UV protection, trafficable areas, agricultural wash down areas, dairy milking sheds, areas that require water blasting.

VerseGrip Rapid Build is water based and environmentally safe, providing an excellent textured coating that is flexible and resists cracking, chipping and aging, with excellent freeze/thaw resistance.

\* Free of Flammable Solvents \* Non-Toxic \* No Voc's \* Low Odour & Water Based

### APPLICATION

VerseGrip Rapid Build is a single component product that may be applied using a roller, squeegee or aggregate spray equipment. VersGrip Rapid Build is applied in thickness from 1.0 - 2.0mm.

VerseGrip Rapid Build should be applied to a dry surface, free of dirt, debris, oil or grease and should not be applied when the ambient temperature is below 10 °C, or if rain is expected within 24 hours of application. With joints or cracks in the surface a reinforcing fabric impregnated with VerseGrip is recommended.

VerseGrip Rapid Build is to be applied at a rate of 1.7kg per 1m<sup>2</sup> for a 1mm dry film thickness coverage. Curing time may vary depending on temperature and relative humidity. VerseGrip Rapid Build cures in 24-48 hours at 25 °C when applied at a dry film thickness of 1.0mm.

### LIMITATIONS

VerseGrip Rapid Build should not be applied when the ambient temperature is below 10 °C. The uncured membrane may be damaged if frozen and should not be applied to wet or frozen surfaces or directly prior to rain. The substrate must contain less than 10% moisture. Please consult technical service with any questions.

### CAUTION

Keep out of reach of children. Avoid storage below 5 °C. Please consult the Safety Data Sheet before using LRM Products VerseGrip Rapid Build.

VerseGrip Rapid Build is mildly alkaline. When applying this product observe normal safety precautions, wear gloves, eye protection and other suitable protective equipment. For further information please consult the product SDS.

## TECHNICAL SERVICE

### Physical Properties (Liquid)

Property	Typical Results
Colour	Black
Specific gravity (liquid) g/cm <sup>3</sup>	Approx. 1.0
Odour	None
Volatile Organic Compound	Contains no solvents
Solids Content	55 - 60%
Viscosity, Brookfield (cps)	10,000 – 15,000
pH	10 - 12

### Performance Data (Cured Membrane)

Property	Typical Results
Colour	Black
Specific gravity, g/cm <sup>3</sup>	Approx. 1.0
Chemical resistance	Resists salt water and many organic and inorganic solutions not recommended for gasoline or other petroleum products.
Tensile Strength ASTM D 412, kPa (psi)	618 (90)
Elongation, %	850%
Adhesion to concrete ASTM C 907, kPa (psi)	765 (111)
Sag flow	None
Low temperature mandrel CGSB 37.58-M86, para. 7.2.6, -15 °C	Pass
Hardness, Durometer Type A	50
Coefficient of friction (static)	0.60
Abrasion resistance	Passed (168)

Proudly



Version: 06/07/2023



Page 2 of 2